1880

Weekly Report of Gold Deposits Melted at United States Mint.

Date.	Assay No.	Name of Depositor.	Weight before Melting. OZ.	DEC.	Weight after Melting. OZ.	DEC.	Loss. OZ.	DEC.	Loss per ct.	Gain. OZ.	DEC.	Description of Bullion.	Notes of Melter & Refiner.
													1/1/80
January 2d	1	G. C. Thompson	29	99	29	99						Bars, Geo.	The deposits for this week are as follows: One of melted lumps from Virginia, with a slight wastage of 0.14%; two bars from Georgia, virtually without wastage; eight others of finer bullion with a moderate wastage of 0.13%; five of base bullion, with a moderate wastage of 8½%; three of dental plate with a very low wastage of 1.29%.
	2	Do	6	51	6	50		01			14	Melted Lps, Va.	
	3	Do	66	07	66	06		01			01	Bars, Geo.	
	4	Do	13	32	11	48	1	84	14		15	Hitch Cases, Pieces, Bars &c.	
	5	Wm H. Lee	49	14	49	08		06			12	Bar	
	6	G. C. Thompson	30	20	28	92	1	28	4		27	Jewelry & Silver	
	7	Do	12	53	11	13	1	40	10		77	Jewelry & Hitch Cases	
	8	Rich.d Helms	33	80	33	75		05			13	Bar	
	9	Hastings & Co.	75	17	75	13		04			05	Buttons & Strips	
	10	Do	55	56	55	50		06			10	Do	
	1	Clark & Haas	5	71	5	71						Bars	
	2	Phillips & Jacobs	26	87	26	87						U. S. Coin	
3d	3	N. C. Gray	16	66	16	55		11			65	Button	
	4	A. Losse	10	54	10	33		21	1		91	Dust & Fillings	
	5	G. C. Thompson	6	49	6	11		38	6		33	Crushed Quartz	
	6	B. Levy	87	23	87	05		18			31	Bars	
	7	D. Rosenthal	8	65	8	02		63	7		00	Jewelry	
	8	J. C. White	16	83	16	54		29	1		71	Dust & Fillings	
	9	Do	16	17	15	77		40			25	Dust & Fillings	
	20	C. & A. Pequignot	39	01	39	00		01			03	Bar	
			609	45	602	49	6	96	1	27			

The first three days in January, 1880.
For week ending 18
Approximate value $ 9,338.59

S. Dobbey Dunpleind
Register.

To the Director of the Mint.

RG104 E-1 Box 120

Report of Gold Deposits
Melted January 2nd & 3rd 1880

RG104 E-1 Box 120

NARA RG104, Entry 1, Box 120

[Abstract:] Report of Gold Deposits Melted January 2nd & 3rd 1880.

Weekly Report of Gold Deposits Melted at United States Mint.

1880

Date.	Assay No.	Name of Depositor	Weight Before Melting Oz. Dec.	Weight After Melting Oz. Dec.	Loss. Oz. Dec.	Loss per ct.	Gain. Oz. Dec.	Description of Bullion.
January 2nd	1	G.C. Thompson	29.99	29.99				Bars, Geo.
	2	Do	6.51	6.50	.01	.14		Melted Lps., Va.
	3	Do	66.07	66.06	.01	.01		Bars, Geo.
	4	Do	13.32	11.48	1.84	14.15		Watch, Cases, Bars & Pieces
	5	Wm. H. Lee	49.14	49.08	.06	.12		Bar
	6	G.C. Thompson	30.20	28.92	1.28	4.27		Jewelry & Silver
	7	Do	12.53	11.13	1.40	10.77		Jewelry Watch Cases
	8	Richd. Nelms	33.80	33.75	.05	.13		Bar
	9	Hastings & Co.	75.17	75.13	.04	.05		Buttons & Strips
	10	Do	58.56	58.50	.06	.10		Do
	1	Clark & Haas	5.71	5.71				Bars
	2	Phillips & Jacobs	26.87	26.87				U.S. Coin
3rd	3	N.C. Gray	16.66	16.55	.11	.65		Button
	4	A. Losse	10.54	10.33	.21	1.91		H.H. & Fillings
	5	G.C. Thompson	6.49	6.11	.38	6.33		Crushed Quartz
	6	B. Leoy	87.23	87.05	.18	.21		Bars
	7	W. Rosenshal	8.65	8.02	.63	7.00		Jewelry
	8	I.C. White	16.83	16.54	.29	1.71		D'TO & Filings
	9	Do	16.17	15.77	.40	.25		D'TO & Filings

	20	C. & A. Pegnignot	39.01	39.00	.01	.03		Bar
			609.45	602.49	6.96	1.27		

Notes of Melter & Refiner.

S 9/1/80

The deposits for this week are as follow: One of melted lumps from Virginia, with a slight wastage of 0.14%; two bars from Georgia virtually without wastage; eight others of finer bullion with a moderate wastage of 0.13%; five of baser bullion, with a moderate wastage of 8 ½ %; three of dental plate with a very low wastage of 1.29%.

Jas. C. Booth
M & R

The first three days in January, 1880.

For week ending ____ 18__

Approximate value, $9,338.59

I. Robley Dungliason
Register.

To the Director of the Mint.